



Gulf Transcrest I

Inhibited Electrical Insulating Oil

Product Description

Gulf Transcrest I is high performance inhibited electrical insulating oil specially designed for use in transformers, switchgears and other electrical equipment. This oil is formulated with high quality severely hydroprocessed naphthenic base oils and fortified with an inhibitor to minimize oxidative change and extend its service life. It possess excellent thermal and oxidation stability, good dielectric properties and heat transfer characteristics due to the low viscosity to provide reliable operation, with reduced down-time and extended service life. **Gulf Transcrest I** exceeds the performance requirements of major transformer and switchgear specifications for inhibited oils.

Features & Benefits

- Excellent thermal stability and oxidation resistance prevents sludge formation, controls deposits and minimises oil degradation leading to reliable operation
- High dielectric strength ensures excellent insulation and quenching of electric arc between switchgear contacts when opening the switch.
- Low power-loss contributes to overall efficiency
- Low viscosity and high interfacial tension ensures good wettability of oil and removal of air gaps to insulate windings and dissipate heat.
- Effective long term protection from rust and corrosion to critical system components

Applications

- Insulating and cooling oil for electrical transformers, switchgears, circuit breakers, capacitors and automotive ignition coils.
- Used where inhibited insulating oils meeting IEC 60296: Inhibited type (I) are required.

Specifications, Approvals & Typical Properties

Meets the following Specifications		
IEC 60296 Inhibited Type (I)		X
Typical Properties		
Test Parameters	Test Method	Typical Values
Viscosity @ 40 °C, cSt	ISO 3104	9.6
Viscosity @ -30 °C, cSt	ISO 3104	1098
Flash Point, PMCC, °C	ISO 2719	148
Pour Point, °C	ISO 3016	-58
Density @ 20°C, Kg/l	ISO 12185	0.873
Breakdown Voltage, kV, Before Treatment	IEC 60156	59
Breakdown Voltage, kV, After Treatment	IEC 60156	75
Acid Number, mg KOH/g	IEC 62021-1	<0.01
DDF @ 90°C	IEC 60247	0.001
Interfacial Tension, mN/m	ASTM D 971	50
Corrosive Sulphur	IEC 62535	Noncorrosive
Sulphur, wt%	ISO 14596	0.005
Antioxidant Additive, wt%	IEC 60666	0.38
Water Content, mg/kg	IEC 60814	10
Oxidation Stability @ 120°C, 500 hrs		
• Total Acidity, mg KOH/g	IEC 61125,C	0.01
• Sludge, %		0.02
• DDF @ 90°C		0.013
PCB Content	IEC 61619	Not Detected

November 2016

Properties mentioned are typical only and minor variations, which do not affect product performance, are expected to arise in normal manufacturing processes. Please follow equipment manufacturer's recommendations for performance level and viscosity grade. The Safety Data Sheet for this product is available from your nearest Gulf Distributor. Please consult our local representative if any further information is required.

The information contained herein is believed to be correct at the time of publication and may be subject to modification from time to time. It is the user's responsibility to verify that this data sheet is current prior to using the product. No warranty expressed or implied is given concerning the accuracy of the information or the suitability of products. Gulf Oil International reserves the right to modify and change its products and specifications without prior notice.

This data sheet has been issued by us in English language only. In the event of any discrepancy between the English language version and any other language version, the English language version shall prevail.